

# weber easy work

## Air entrainer and plasticiser mortar additive

Technical Data Sheet  
Issued on : 28.04.2016  
Revision No: 001

### ■ Description

Air entrainer and plasticiser mortar additive that improves workability of renders, screeds and similar mortars, ready to use in construction sites.

### ■ Advantages

- Practical and ready to use
- Improved workability of mortar
- Decreasing mortar loss

### ■ Range of application

- Applied at the screeds and renders of any kinds of building foundations, basements, retaining walls, culverts, tunnels, swimming pools, terraces and similar structures.

### ■ Conditions of application

- Ambient temperature is between +5 °C and +35 °C.
- Sand should be clean, cement should be fresh and not deteriorated which is to be used in mixture.

### ■ Reference standards

- Public Works Pos. No: 04.379/A04

### ■ Application

- **weber easy work** should be shaken well before application.
- **weber easy work** should be added in clean mixture water and mixed.
- Mixture with **weber easy work** should be added in dry mixture.
- When mixing will be done by hand, amount of additive should be increased.

### ■ Consumption

Product	Consumption
<b>weber easy work</b>	% 0,5 of cement amount: (0,5 lt for 100 kg. cement )  <b>Note:</b> Suggested amounts are just for reference. Changes may occur according to the aggregate, cement, ambient temperature at the jobsite

### ■ Packaging

5 ve 20 lt. plastic drums.

### ■ Color

Light yellow.

### ■ Shelf life

2 years as of the production date in dry and moisture-free environment provided that packages will not be opened and kept between 5 °C and 35 °C. Package should be kept tightly closed when not in use.

- > The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.
- > **Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş.** is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.



Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.  
Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No: 284 • 35730 Kemalpaşa • İzmir • Türkiye  
Tel: +90 (232) 397 07 00 • www.weber.com.tr • info@weber.com.tr • Çözüm hattı: 444 6 990

