

weber.therm maxiplast

Render for weber maxitherm thermal insulation system

Technical Data Sheet

Issued on : 05.10.2015

Revision No.: 002

■ Description

Cement-based, polymer modified render for **weber.maxitherm thermal insulation system**.

■ Advantages

- In conformity with ETAG 004*.
- Ensures perfect adherence to thermal insulation panels.
- Resistant to thermal shocks.
- Easy to apply and forms smooth surfaces.

■ Range of application

- Applied as substrate render on **weber.therm maxipower** thermal insulation panels at all buildings.

■ Application substrates

- On interior and exterior walls;
 - **weber.therm maxipower** thermal insulation panels.
- Please consult us for all other application substrates.

■ Application properties

- Pot life: 3 hours
- Application thickness: 4 mm
- Coat thickness: Max. 2 mm
- Time between the coats: 3-4 hours
- Time to wait for final coat application of **weber.therm maxiplast**: min. 7 days.

■ Performance

- Mass per unit volume of fresh mortar: 1500 ± 100 kg/m³
- Porous density of hardened cement-based render: 1300 ± 200 kg/m³
- Granulometry: the percentage left on the 1 mm sieve $\leq 1,0$
- Compression strength: ≥ 6 N/mm²
- Adhesion strength with the isolation panel: $\geq 0,08$ N/mm²
- Water absorption: $\leq 0,5$ kg/m².dk^(0,5)
- Water vapor permeability: $\mu \leq 15$
- Thermal resistance: $\leq 0,45$ W/mk

These values were obtained as a result of laboratory tests and they are valid for performance of finished applications at the end of drying time. Values may vary due to differences in ambient jobsites.

■ Reference standards

- TSEK 113
- Public Works No: 04.481.

■ Attention points

- Dilatation joints should not be covered with **weber.therm maxiplast**, dilatation profile should be used for these parts.

■ Preparation of substrate

- The insulation panel should be clean, dry and be bonded on the lower substrate well.
- The gaps between panels should be filled with the same insulation material or foam as per the width, the protrusions to occur should be cleared to reduce the consumption of **weber.therm maxiplast**.

■ Conditions of application

- Ambient temperature is between +5 °C and +30 °C.
- Avoid application in very damp and/or hot weather, under the sunlight.
- It should not be used on substrates which are frozen or melting or have the risk of frost or rain within 24 hours.

■ Application

- Average 6,5 lt clean water and 25 kg bag. **weber.therm B1 maxiplast** should be mixed with a low-speed mixer or trowel preferably well as there will be no pellet.
- The mortar should be aged for 10 minutes before application.
- **weber.therm B1 maxiplast** should be applied on the substrate via steel trowel.
- Glass-fiber mesh should be placed by pressing upward to downward and stretching, without folding and as to be at the same distance from insulation panel to the whole surface before **weber.therm maxiplast** dries.
- To avoid cracks, glass-fiber mesh should be applied by overlapping as 10 cm at joining points.
- The glass-fiber mesh should be turned at least 20 cm in the corners and around all beams, window and door frames.
- Second hand of application should be started after 3-4 hours.
- After the application, the surface will be ready for exterior coating.

■ Consumption

5 kg/m².

■ Packaging

Net 25 kg bag,
(64 units in pallet, 1600 kg).

■ Pallet size

107 x 107 cm.

■ Color

Grey.

■ Application tools

Hand mixer, steel trowel, glass-fiber mesh.

■ Shelf life

1 year as of the production date in dry and moisture-free environment provided that packages will not be opened.

Package should be kept tightly closed when not in use.

FOR INFO

- The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.
- **Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş.** is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.



Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.
KemaIpaşa OSB Mah. Kuyucak Yolu Sokak No: 284 • 35730 KemaIpaşa • İzmir • Türkiye
Tel: +90 (232) 397 07 00 • www.weber.com.tr • info@weber.com.tr • Çözüm hattı: 444 6 990

