

weber.kol seraçım max

Tile adhesive

Technical Data Sheet

Issued on : 22.11.2018

Revision No: 009

■ Description

Cement based tile adhesive with reduced slip.

■ Advantages

- Easy application
- Safe use in tile application

■ Range of application

- Used for fixing ceramic, tile and similar coating materials on interior walls, floors. Bonding of aerated concrete and any other high water absorbing construction elements.

■ Application substrates

- Interior walls:
 - Cement based render;
- Interior floors;
 - Cement based screed,
 - Concrete floor,
- Exterior floors;
 - Cement based screed,
 - Concrete floor.

Please see current "weber solution guide" "product selection tables for substrate types and max. coating sizes to be applied with **weber.kol seraçım max**

- Please consult us for all other application substrates.

■ Limits of application

- Not applicable on metal surfaces (**weber EP 800** should be used).
- Not applicable on floors with heavy traffic (e.g.: industrial areas) (**weber.kol flex konfor konsantre** or **weber.kol flex extra** should be used).
- Not applicable on wooden floors, old painted substrates, swimming pools and present tile coating. (See current weber solution guide*).
- Not applicable on gypsum plaster, concrete wall, gypsum board and gypsum block substrates (See current "weber solution guide").

■ Application properties

- Pot life: max. 4 hours,
- Open time: max. 20 minutes,
- Adjustability: max. 15 minutes,
- Time required for grouting: 24 hours (wall), 48 hours (floor),
- Time required for foot traffic: 24-48 hours,
- Application thickness: 3 to 10 mm (one or both sides applications).

■ Performance

- Initial tensile adhesion strength: $\geq 0,5 \text{ N/mm}^2$
- Tensile adhesion strength after water immersion: $\geq 0,5 \text{ N/mm}^2$
- Tensile adhesion strength after heat aging: $\geq 0,5 \text{ N/mm}^2$

- Tensile adhesion strength after freeze-thaw cycles: $\geq 0,5 \text{ N/mm}^2$
- Open time tensile adhesion strength: $\geq 0,5 \text{ N/mm}^2$ after not less than 20 min.
- Slip: $\leq 0,5 \text{ mm}$.
- Heat resistance: between $-30 \text{ }^\circ\text{C}$ and $+60 \text{ }^\circ\text{C}$.

These values were obtained as a result of laboratory tests and they are valid for 28 days performance of finished applications. Values may vary due to differences on job-sites.

■ Reference standards

- TS EN 12004/CIT class
- CE
- Public Works Pos No: 04.380/001

Please see current "weber solution guide" for the classification introduced by TS EN 12004 norm about tile adhesives.

■ Attention points

- Never add foreign materials.
- All tools should be cleaned with water before drying after the application.

■ Preparation of substrates

- The surface should be dry, smooth and durable. Plasters thinner than 3 mm on the substrate should be scraped and cleaned thoroughly.
- Porous substrates should be wetted.
- Wait until the water layer disappears as the floor will remain damp.
- Important deformations or holes on the substrate should be repaired with **weber.rep MA 200** minimum 24 hours before the application of **weber.kol seraçım max**
- Local repairs thinner than 7 mm can be done by use of **weber.kol seraçım max**.

■ Conditions of application

- Ambient temperature is between $+5 \text{ }^\circ\text{C}$ and $+35 \text{ }^\circ\text{C}$.
- It should not be used on substrates which are frozen or melting or have the risk of frost within 24 hours.
- Avoid application under direct sunlight, strong wind or hot surfaces.
- Avoid film formation by **weber.kol seraçım max** during application, if film is present, that area should be notched again.

■ Application

- Average 6,75-7,25 lt. water and 25 kg **weber.kol seraçım max** should be mixed with low-speed mixer preferably or trowel until no more lump will remain.

- After aging **weber.kol seraçim max** for 5 minutes, it should be mixed for further 1-2 minutes before application.
- The mortar should be applied on the substrate and its thickness should be adjusted with steel notched trowel. Tooth size of trowel should be adjusted according to dimensions of tile and smoothness of application substrate.
- Mortar should be applied on both application substrate and backside of tiles below mentioned sizes (double-sided adhesion).
 - Interior floor applications:
Tiles bigger than 1100 cm²
 - Interior wall applications:
Tiles bigger than 500 cm²
 - All exterior floor applications.
- For good adhesion force should be applied by means of rubber hammer and air should be ejected.

■ Consumption

Tile dimensions	Notched trowel	Consumption
120 cm ²	6x6x6 mm.	One-sided adhesion 4 kg./m ² Double -sided adhesion 5-6 kg./m ²
120 cm ² and 500 cm ²	8x8x8 mm.	One-sided adhesion 5 kg./m ² Double -sided adhesion 6,5 kg./m ²
500 cm ² and 2000 cm ²	10x10x10 mm.	one-sided adhesion 5,5 kg./m ² double-sided adhesion 7-8 kg./m ²

■ Packaging

Net 25 kg bag (64 bags in pallet, 1600 kg).

■ Pallet size

107 x 107 cm.

■ Color

Grey.

■ Application tools

Hand mixer, trowel, rubber hammer, steel notched trowel.

■ Shelf life

1 year as of the production date in dry and moisture-free environment provided that packages will not be opened.

Package should be kept tightly closed when not in use.

Package should be protected against frost.

- > The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.
- > **Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş.** is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.



Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.
Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No: 284 • 35730 Kemalpaşa • İzmir • Türkiye
Tel +90 (232) 397 07 00 • www.weber.com.tr • info@weber.com.tr • Çözüm hattı: 444 6 990

