

weberjoint flex

Cement based, flexible high performance, colored joint grout mortar

Technical Data Sheet:

Issued on 12.08.2024

Revision No: 011

Description

Cement based, flexible high performance, colored joint grout mortar.

Reference standards

- TS EN 13888-1 / CG2WA class
- G marking
- Public Works Pos No: 10.300.2232

Advantages

- Resistant to fungus, mould and algae.
- On floors subject to heavy traffic and heating floors, In tile applications on tile.

Range of application

- Used for grout applications up to 12 mm width of coating materials such as ceramic, marble, granite, granite ceramic and similar coating materials.

Application substrates

- On interior and exterior wall and floor,
- Private and medium scaled swimming pools,
- Tile renovations,
- All areas requiring specific application.
- Please consult us for all other application substrates.

Preparation of substrates

- Dust, chip, construction and cement residuals, etc. to be between the gaps of grouts should be cleaned by scrapping with a thin stick and brush to ensure a homogenous color and drying.
- Joint gaps should be moistened especially on walls before the application.

Conditions of application

- Ambient temperature is between +5 °C and +35 °C.
- It should not be used on substrates which are frozen or melting or have the risk of frost within 24 hours.
- Avoid application under direct sunlight, strong wind or (heated) hot surfaces.
- Underfloor heated flooring in a hot state should not be applied to floor and the system should be turned off 24 hours before application.

Application

- Average 5,4-5,8 lt water and 20 kg **weberjoint flex** should be mixed with low-speed mixer preferably or trowel as there will be no lumps.
- weberjoint flex** should be mixed for further 1-2 minutes after aging for 10 minutes before the application.
- The mortar should be filled in the joints with hard rubber spatula or trowel.
- It should be applied firstly parallel and then in crosswise direction to fill the joints thoroughly.

- The excessive mortar on the substrate should be scraped with soft-tip trowel or damp sponge- tip trowel and it should be wiped with a damp sponge after waiting for 15-30 minutes depending on ambient temperature and thin joint layer to be on the substrate should be cleaned thoroughly.
- The process of leveling and cleaning the substrate should be done via a dry cloth when **weberjoint flex** is still wet

Application tools

Hand mixer, trowel, rubber-tip trowel, sponge-tip trowel, rubber spatula, sponge, brush.

Consumption

Ceramic size	Ceramic dept	Joint width			
		3 mm (gr./m ²)	6 mm (gr./m ²)	8 mm (gr./m ²)	12 mm (gr./m ²)
20x20	8 mm	375	750	1000	1500
25x40	8 mm	250	500	670	1000
33x33	8 mm	225	450	600	900
60x60	10 mm	165	330	440	660
60x120	10 mm	110	220	290	435

Attention points

- Not applicable on areas subject to high pressure (>100 bar) and chemicals and requiring hygiene (See current "weber solution guide").

The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.
, Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.

Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.

Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No:284 • 35730 Kemalpaşa • İzmir • Türkiye
Tel: +90 (232) 397 07 00 • www.trweber • info@trweber • Çözüm Hattı 444 6 990

 **weber**
SAINT-GOBAIN

■ Technical Information

Product	weberjoint flex
Product Type	Powder
Color	25 color option(for 20 kg bag)
Packaging	20 kg kraft bag
Application features	
Pot life	Max. 1 hours
Setting time	12 hours
Time required for opening floor to traffic	24-48 hours.
Performance	
Abrasion resistance	≤ 1000 mm ³
Flexural strength	≥ 2,5 N/mm ²
Compressive strength	≥ 15 N/mm ²
Shrinkage	≤ 3 mm/m
Water absorption (30 min. later)	≤ 2 g.
Water absorption (240 min. later)	≤ 5 g.

These values were obtained as a result of laboratory tests and they are valid for 28 days performance of finished applications. Values may vary due to differences on job-sites.

■ Storage

Packaging	• In a net bag of 20 kg(80 pieces of 1600 kg in a pallet)
Shelf life	• 1 year as of the production date in dry and moisture- free environment provided that packages will not be opened. • Package should be kept tightly closed when not in use. Package should be protected against frost.

■ Safety Precautions

- Use the appropriate safety equipment (dust mask, gloves).
- Protect your eyes / face.
- Avoid contact with eyes and skin.
- In case of contact with eyes, rinse immediately with plenty of water and consult a specialist.
- Read the Material Safety Data Sheet for more detailed

Legal Warning

Since there are different conditions and requirements that apply in any case, Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş. cannot be liable for other than the information provided in this product datasheet.

Access detailed documentation of the product by scanning QR or tr.weber



The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.
Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.

Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.

Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No:284 • 35730 Kemalpaşa • İzmir • Türkiye
Tel: +90 (232) 397 07 00 • www.tr.weber • info@tr.weber • Çözüm Hattı 444 6 990

weber
SAINT-GOBAIN