

weberkol serakol

Cement based tile adhesive mortar with improved water-resistance quality, reduced slip and extended open time

Technical Data Sheet:
Issued on 28.09.2021
Revision No: 011

■ Description

Cement based tile adhesive mortar with improved water-resistance quality, reduced slip and extended open time.

■ Reference standards

- TS EN 12004/CITE class
- CE
- Public Works Pos No: 10.300.2202
- Please see current "weber solution guide" for the classification introduced by TS EN 12004 norm about tile adhesives.

■ Advantages

- Safe and durable adhesion with polymer additive.
- Suitable for laying on the wall from top to bottom.
- Long working time
- Improved water impermeability

■ Range of application

- Used for fixing ceramic, tile, glass mosaic and similar coating materials to wall and floor in wet areas such as especially bathroom, kitchen at interior and exterior floors.

■ Application substrates

- **Interior walls:**
 - Cement based render, (**weberprim art** applied).
- **Interior floors;**
 - Cement based screed,
 - Concrete floor,
- **Exterior floors;**
 - Cement based screed,
 - Concrete floor.
- Please see current "weber solution guide" "product selection tables" for substrate types and max. coating sizes to be applied with **weberkol serakol**
- Please consult us for all other application substrates.

■ Preparation of substrates

- The surface should be dry, smooth and durable. Plasters thinner than 3 mm on the substrate should be scraped and cleaned thoroughly.
- Porous substrates should be wetted. Wait until the water layer disappears as the floor will remain damp.
- Important deformations or holes on the substrate should be repaired with **weberrep** structural repair mortars minimum 24 hours before the application of **weberkol serakol**
- Local repairs thinner than 7 mm can be done by use of **weberkol serakol**.

■ Conditions of application

- Ambient temperature is between +5 °C and +35 °C.
- It should not be used on substrates which are frozen or melting or have the risk of frost within 24 hours.
- Avoid application under direct sunlight, strong wind or hot surfaces.
- Avoid film formation by **weberkol serakol** during application, if film is present, that area should be notched again.

■ Application

- For grey colour average 6,25-7,75 lt water and for white colour average 7,25-7,75 lt water and preferably 25 kg kraft bag
- **weberkol serakol** should be mixed with low-speed mixer preferably or trowel until no more lump will remain.
- After aging **weberkol serakol** for 5 minutes, it should be mixed for further 1-2 minutes before application.
- The mortar should be applied on the substrate and its thickness should be adjusted with steel notched trowel. Tooth size of trowel should be adjusted according to dimensions of tile and smoothness of application substrate.
- Mortar should be applied on both application substrate and backside of tiles with consumption table mentioned size (back buttering).
- **Interior floor applications:** Tiles bigger than 200cm²
- **Interior wall applications:** Tiles bigger than 1800cm²
- **All exterior floor applications.**
 - For good adhesion force should be applied by means of rubber hammer and air should be ejected.
 - In applications, weight of the coating is as important

■ Application tools

Hand mixer, trowel, rubber hammer, steel notched trowel.

■ Consumption

weberkol serakol	4-6 kg./m ²
-------------------------	------------------------

■ Attention points

- This product is not used on metal surface floors subject to heavy traffic, prefabricated and underfloor heated floors, old painted surfaces, swimming pools, existing ceramic coating, gross concrete, plasterboards walls, surfaces exposed to climatic changes and subjected to difficult conditions and on terraces and outdoors that will be directly contact with the sun.
- 'C2' class ceramic tile should be used in applications on plaster panel.
- Never add foreign materials.
- Attention should be paid to the proportion of water that is written on the bag. Adding too much or too little water to the product reduces the performance of the product

The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures. Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.

Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.

Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No:284 • 35730 Kemalpaşa • İzmir • Türkiye
Tel: +90 (232) 397 07 00 • www.tnweber • info@weber.com.tr • Çözüm Hattı 444 6 990

weber
SAINT-GOBAIN

- White **weberkol serakol** should be used for light ceramic and similar coatings.

■ Technical information

Product	weberkol serakol
Product Type	Powder
Colour	White and Grey
Packaging	25 kg kraft bag (64 bags in pallet, 1600
Application features	
Pot life	Max 4 hours
Open time	Max 25 minutes
Adjustability	Max 20 minutes
Time required for grouting	24 hours (wall and floors)
Time required for foot traffic	24 hours
Application thickness	3 to 10 mm (one or both sides)
Performance	
Fire response class	A1
Initial tensile adhesion strength	$\geq 0,5\text{N/mm}^2$
Tensile adhesion strength after water immersion	$\geq 0,5\text{N/mm}^2$
Tensile adhesion strength after heat aging	$\geq 0,5\text{N/mm}^2$
Tensile adhesion strength after freeze-thaw cycles	$\geq 0,5\text{N/mm}^2$
Extended open time:tensile adhesion strength :not less than 30 min.	$\geq 0,5\text{N/mm}^2$
Slip	$\leq 0,5$ mm
Heat resistance	between -15°C and $+70^{\circ}\text{C}$.

The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.
, Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.

■ Storage

Packaging	• 25 kg kraft bag (64 bags in pallet, 1600 kg).
Shelf life	• 1 year as of the production date in dry and moisture- free environment provided that packages will not be opened. • Package should be kept tightly closed when not in use. Package should be protected against frost.

■ Safety Precautions

- Use the appropriate safety equipment (dust mask, gloves).
- Protect your eyes / face.
- Avoid contact with eyes and skin.
- In case of contact with eyes, rinse immediately with plenty of water and consult a specialist.
- Read the Material Safety Data Sheet for more detailed

Legal Warning

Since there are different conditions and requirements that apply in any case, Saint-Gobain Weber Yapı Kimyasalları San. ve Tic A.Ş. cannot be liable for other than the information provided in this product datasheet.

These values were obtained as a result of laboratory tests and they are valid for 28 days performance of finished applications. Values may vary due to differences on job-sites.