

weberkol flex pool

Cement based flexible tile adhesive with reduced slip, extended open time and improved with additional qualities

Technical Data Sheet:
Issued on 19.09.2022
Revision No: 001

■ Description

Cement based flexible tile adhesive with reduced slip, extended open time and improved with additional qualities.

■ Reference standards

- TS EN 12004/C2TES1 class.
- CE
- Public Works Pos No: 10.300.2204

■ Advantages

- Safe dhesion for all type of swimming pools
- High performance on pedestrain and freight traffic

■ Range of application

- Used for fixing ceramic, granite ceramic, glazed porcelain at interior and exterior walls and floors;
- Used in areas with heavy pedestrian and freight traffic.
- Suitable for use in terrace and balcony applications.
- Used in private, public and heated swimming pools.

■ Application substrates

Interior floors;

- Cement based screed,
- Concrete floor,
- Floor heating systems,

Exterior floors;

- Cement based screed,
- Concrete floor,

Interior walls;

- Cement based render
- Gypsum block, gypsum board and gypsum plaster (**weberprim art** applied)

- Concrete

- Existing tile (**weberprim TG 5** or **weberprim ADR** applied),

Exterior walls;

- Cement based render
- Concrete
- Cement based render and screed

■ Preparation of substrates

- The surface should be dry, smooth and durable. Plasters thinner than 3 mm on the substrate should be scraped and cleaned thoroughly.
- Porous substrates should be wetted. Wait until the water layer disappears as the floor will remain damp.
- Important deformations or holes on the substrate should be repaired with **weberep** structural repair mortars minimum 24 hours before the application of **weberkol flex pool**
- Local repairs thinner than 7 mm can be done by use of **weberkol flex pool**

■ Application

- For white colour average 6,75 lt., for grey colour average 7,75 of water and preferably 25 kg kraft bag **weberkol flex pool** should be mixed with low-speed mixer preferably or trowel until no more lump will remain.
- After aging **weberkol flex pool** for 5 minutes, it should be mixed for further 1-2 minutes before application.
- The mortar should be applied on the substrate and its thickness should be adjusted with steel notched trowel. Tooth size of trowel should be adjusted according to dimensions of tile and smoothness of application substrate.
- Mortar should be applied on both application substrate and backside of tiles below-mentioned sizes (back buttering).

For granite ceramic, glazed porcelain, natural composed stone, etc:

•Interior floor applications:

Tiles bigger than 500 cm²

•Interior wall applications:

Tiles bigger than 120 cm²

For ceramic, tile etc:

•Interior wall and floor applications:

Tiles bigger than 1100 cm²

•All exterior wall and floor applications.

- For good adhesion force should be applied by means of rubber hammer and air should be ejected
- In applications, weight of the coating is as important as the size.

■ Consumption

4-6 kg./m²

■ Application tools

Hand mixer, trowel, rubber hammer, steel notched trowel

■ Conditions of application

- Ambient temperature is between +5 °C and +35 °C.
- It should not be used on substrates which are frozen or melting or have the risk of frost within 24 hours.
- Avoid application under direct sunlight, strong wind or hot surfaces.
- Avoid film formation by **weberkol flex pool** during application, if film is present, that area should be notched again.

The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures. Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.

Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş.

Kemalpaşa OSB Mah. Kuyucak Yolu Sokak No:284 • 35730 Kemalpaşa • İzmir • Türkiye
Tel: +90 (232) 397 07 00 • www.tnweber • info@weber.com.tr • Çözüm Hattı 444 6 990

weber
SAINT-GOBAIN

■ Attention points

- This product is not used on metal surface (**weberep 800** or **weberep easy** should be used)
- Never add foreign materials
- Attention should be paid to the proportion of water that is written on the bag. Adding too much or less water to the product reduces the performance of the product
- White **weberkol flex pool** should be used for light ceramic glazed porcelain and similar coatings

■ Technical Information

Product	weberkol flex pool
Product Type	Powder
Colour	Grey and white
Packaging	25 kg kraft bag (64 bags in pallet, 1600 kg)
Application features	
Pot life	Max 4 hours
Open time	Max. 30 minutes
Adjustability	Max. 20 minutes
Time required for grouting	24 hours (on floor and wall).
Time required for foot traffic	24 hours
Application thickness	3 to 10 mm (one or both sides)

Performance	
Performance fire response class	A1
High tensile adhesion strength	≥ 1 N/mm ²
High tensile adhesion strength after water immersion	≥ 1 N/mm ²
High tensile adhesion strength after heat aging	≥ 1 N/mm ²
High tensile adhesion strength after freeze-thaw cycles	≥ 1 N/mm ²
Extended open time after not less than 30 min)	≥ 0,5 N/mm ²
Transverse deformation	2,5 mm ≤SI <5 mm
Slip	≤ 0,5 mm
Heat resistance	between -15°C and +70 °C.

These values were obtained as a result of laboratory tests and they are valid for 28 days performance of finished applications. Values may vary due to differences on job-sites.

■ Storage

Packaging	• 25 kg kraft bag (64 bags in pallet, 1600 kg).
Shelf life	• 1 year as of the production date in dry and moisture- free environment provided that packages will not be opened. • Package should be kept tightly closed when not in use. Package should be protected against frost.

■ Safety Precautions

- Use the appropriate safety equipment (dust mask, gloves).
- Protect your eyes / face.
- Avoid contact with eyes and skin.
- In case of contact with eyes, rinse immediately with plenty of water and consult a specialist.
- Read the Material Safety Data Sheet for more detailed

Legal Warning

Since there are different conditions and requirements that apply in any case, Saint-Gobain Weber Yapı Kimyasalları San. ve Tic. A.Ş. cannot be liable for other than the information provided in this product datasheet.

*The stated times apply for 20 °C substrate and ambient temperature and increase at lower temperatures and decrease at high temperatures.
, Saint-Gobain Weber Yapı Kim. San. ve Tic. A.Ş. is not responsible for the application errors arising from use of product beyond its intended purpose or failure to comply with the foregoing application conditions and advice on the product.*